


CLAIMS

1. A negative resist composition comprising at least an alkali-soluble resin, a cross-linking agent which is cross-linked with
 5 the alkali-soluble resin by the action of an acid, and an onium salt as a photoacid generator, in which the anion component of the onium salt is at least a sulfonate having a polycyclic structure.
- 10 2. The negative resist composition according to claim 1 further comprising an acidic compound and/or a basic compound.
3. The negative resist composition according to claim 1 or 2, wherein the polycyclic structure is at least one selected from
 15 a group consisting of adamantane, tricyclodecane, tetracyclodecane, isobornyl, norbornane, adamantane alcohol, norbornane lactone, and derivatives thereof.
4. The resist composition according to any one of claims 1 to
 20 3, wherein the anion component of the onium salt is a sulfonate represented by the following general formula (1).



5. The negative resist composition according to any one of claims 1 to 4, wherein the cation component of the onium salt is an iodonium salt.

5

6. A method for forming a resist pattern comprising the steps of: forming at least a photoresist layer on a substrate using the negative resist composition according to any one of claims 1 to 5, and forming the desired photoresist pattern by applying exposure and development processes to the photoresist layer.

10